



比亚迪股份有限公司
BYD COMPANY LIMITED

**SPECIFICATION FOR
HIGH TEMPERATURE NI-CD CELL
APPROVAL SHEET**

TO : _____
BYD MODEL NO : D-SC1700H
CUSTOMER APPROVED P/N : _____
DATE OF SUBMISSION : 08-Oct-11
ATTACHMENT : SPECIFICATION
TOTAL NO. OF PAGES : 5
SPECIFICATION NO : S-DSC1700H01
VERSION NO : 1.0

Drawn	CUI-MIAO	
Approved	Customer Dept. I	<i>GUOQING-LI</i>
	Technology Dept. I	<i>ZHENGYI-HUANG</i>
	Quality Control Dept. I	<i>DONGXU-CHEN</i>

(with company chop)
Please sign and return one copy to us

BYD COMPANY LIMITED

ADD:BYD Scien-Tech Industrial Center Yan'an Road
Kuichong, Longgang, Shenzhen China P.C.: 518119
TEL: 86-755-89888888 FAX: 86-755-84202222
E-Mail:byd@byd.com
<http://www.byd.com.cn>

-Confidential. Please keep integrated.-
The content of this document is the property of BYD Company Limited. It is to be treated strictly confidential and is not to be disclosed, reproduced, or used in whole or in part without written consent.

1. APPLICATION

This specification applies to the Ni -Cd batteries.

Model : D-SC1700H

2. CELL AND TYPE

2.1 Cell : Sealed Ni –Cd Cylindrical Cell.

2.2 Type : D-SC1700H

2.3 Size type: SC

2.4 IEC type: KR23/43

3. RATINGS

3.1 Nominal voltage : 1.2 V

3.2 Nominal capacity : 1700 mAh/0.2CmA

3.3 Typical weight : 45 g (unit cell)*

“*”:Battery weight is only for reference.

3.4 Standard charge : 170 mA(0.1C)×15hours

3.5 Rapid charge : 850 mA×2.5hours(Max.)

3.6 Trickle charge : 85 mA(0.05C)×48hours

3.7 Discharge cut-off voltage : 1.0 V(0.2CmA)

3.8 Temperature range for operation (Humidity: Max. 85%)

Charge 5~ +70℃ (Note 2)

Discharge 5~ +70℃ (Note 2)

3.9 Temperature range for storage (Humidity: Max. 85%)

Within 2 years -2 0~+35℃ (Note 3)

Within 6 months -2 0~+55℃

Within a month -2 0~+60℃

3.10 Storage duration before use: Less than 6 months from batteries received to start with charging.

Note1: Rated capacity figures are based on single cell performance.

Note2: Max continuous temperature is 50℃, more than 50℃ for charge and discharge occasionally is accepted.

Note3: We recommend cells or batteries are charged and discharged at least once every 6 months.

Note4: Never over discharge the battery.

Note5: If there are any conflict between specification and other standards, please use the specification as the final standard.

-Confidential. Please keep integrated.-

The content of this document is the property of BYD Company Limited. It is to be treated strictly confidential and is not to be disclosed, reproduced, or used in whole or in part without written consent.

4. PERFORMANCE**4.1 TEST CONDITIONS**

The test is carried out with new batteries.(within a month after delivery)

Ambient conditions

Temperature : +20±5 °C

Humidity : 65±20%

Standard charge :170mA(0.1C)×15hrs

Standard discharge :0.2C to 1.0V

4.2 TEST METHOD & PERFORMANCE

Test	Unit	Specification	Conditions	Remarks
Capacity	mAh	≥1700	Standard charge/discharge	up to 3 cycles are allowed
Open Circuit Voltage(OCV)	Voltage (V)	≥1.25	After 1 hour standard charge	
Internal impedance	mΩ/cell	≤12	Upon fully charge (1KHz)	
High rate discharge(1C)	minute	≥48(1360mAh)	Standard charge before discharge	End Voltage is 1.0V/Cell
Discharge time after overcharge	hour	≥4.25	85 mA(0.05C) charge 28days,then discharge at 0.2C to 1.0V	Ambient TEMP 25°C±2°C
Charge Retention	mAh	≥1190	standard charge; storage: 28 days Standard discharge	
Leakage		No leakage nor	Fully charge at 850	
IEC Permanent Charge Test	hr	3.75(Cycle No.2&3) 2.50(Cycle No.8&9)	IEC61951-1(2003)7.4.2.3	See Note 6

4.3 Humidity

The cells shall not leak during the 14 days when it is submitted to the condition of a temperature of 33±3 °C and a relative humidity of 80±5% (salting is allowed).

4.4 Vibration

Cells shall be mechanically and electrically normal after vibration which has an amplitude of 4mm(0.1575 inches) a frequency of 1000 cycles per minute, which should be continued in any directions during 60 minutes

4.5 Shock

Cells shall be mechanically and electrically normal after being subjected to a drop from a height of 450mm (17.716inches) onto an oak board in a voluntary axis respectively 3 times.

-Confidential. Please keep integrated.-

The content of this document is the property of BYD Company Limited. It is to be treated strictly confidential and is not to be disclosed, reproduced, or used in whole or in part without written consent.

4.6 Short

Cells shall not explode after 1 hour short-circuit test.

4.7 Incorrect polarity charging

Cells shall not explode after 5 hour of incorrect polarity charging at 0.5 CmA.

5. PRECAUTION

5.1 We recommend you to set the cut-off voltage at 1.0V/cell.

5.2 If the cut-off voltage is above 1.1V/cell, cells may be underutilized resulting insufficient use of the available capacity.

5.3 If it is below 1.0V/cell, cells may have over-discharged or reverse charged.

5.4 Do not detect $-\Delta V$ for first 5 minutes of charging.

5.5 The cells shall be delivered in discharged condition, Before testing or using, the cells shall be correctly charged in accordance with this specifications.

6. WARNING

6.1 Avoid direct soldering onto cells.

6.2 Observe correct polarity when connecting.

6.3 Do not charge with more than our specified current.

6.4 Use only within the specified working temperature range.

6.5 Do not subject cells or batteries to mechanical shock.

6.6 Do not mix cells of different manufacture, capacity, size or type within a battery.

6.7 Seek medical advice immediately if a cell or battery has been swallowed.

6.8 When disposing of secondary cells or batteries, keep cells or batteries of different electro-chemical systems separate from each other.

6.9 Do not maintain secondary cells and batteries on charge when not in use.

7. DANGER!

7.1 Avoid throwing cells into a fire or attempting to disassemble them. As the electrolyte inside is strong alkaline and can damage skin and clothes.

7.2 Avoid short circuiting. It may be leakage.




Note 6:

IEC61951-1(2003) 7.4.2.3 Permanent Charge Endurance Test

Cycle No.	Ambient Temperature	Charge	Discharge	Requirement
1	40°C	0.05C x 48hrs	0.2C to 1.0V/cell	N/A
2~3	40°C	0.05C x 24hrs	0.2C to 1.0V/cell	Discharge Time:3.75hrs
4	70°C	0.05C x 60days	0.2C to 1.0V/cell	N/A
5~6	70°C	0.05C x 60days	0.2C to 1.0V/cell	N/A
7	40°C	0.05C x 48hrs	0.2C to 1.0V/cell	N/A
8~9	40°C	0.05C x 24hrs	0.2C to 1.0V/cell	Discharge Time:2.50hrs


-Confidential. Please keep integrated.-


The content of this document is the property of BYD Company Limited. It is to be treated strictly confidential and is not to be disclosed, reproduced, or used in whole or in part without written consent.



DATE CODE:

L 40
Year(2011) Week(40)



						 比亚迪股份有限公司 BYD COMPANY LIMITED			
						DRAWN	CUI-MIAO	DATE	2011/10/08
						CHECKD	GUOQING-LI	DATE	2011/10/08
						APPROVED	JIANGUO-TANG	DATE	2011/10/08
2	PAPER TUBE	SC	1		10028994-00				
1	CELL	SC	1	NI-CD					
NO.	NAME	SIZE	QTY	NOTE	SAP NO	SCALE	/	UNIT	MM