

ARTS ENERGY

ARTS Energy's VNT high temperature Ni-Cd series are perfectly suited to emergency and security equipment applications. It is designed to accept a permanent charge for a minimum of 4 years in high temperature environments (up + 40°C).

To meet customers' requirements, ARTS Energy provides custom-designed and standardised battery packs.

For your battery design and system needs, please contact ARTS Energy's engineers.



ELECTRICAL CHARACTERISTICS

Nominal voltage (V)	1.2
Typical capacity (mAh)*	4250
IEC minimum capacity (mAh)*	4000
IEC designation	KRMT 33/62
Impedance at 1000 Hz (mΩ)	6

* Charge 16 h at C/10, discharge at C/5.

DIMENSIONS

Diameter (mm)	32.15 ± 0.1
Height (mm)	59.9 ± 0.4
Top projection (mm)	3.1 ± 0.4
Top flat area diameter (mm)	5.6
Weight (g)	119

Dimensions are given for bare cells.

CHARGE CONDITIONS	Time (h)	Temp. (°C)	Current
Standard	16	+5 to +40	C/10
Permanent		+5 to +40	C/20

DISCHARGE CONDITIONS	Temp. (°C)	Current
	+5 to +40	12A max

CYCLING CONDITIONS

ELU applications	1 discharge / month MAX
Back up applications	Consult ARTS Energy

APPLICATIONS

- Emergency lighting
- Memory back-up systems
- Security devices

MAIN BENEFITS

- Permanent charge
- Good charge efficiency at high temperature
- Superior robustness
- Long life duration

TECHNOLOGY

- Plastic bonded positive electrode
- Plastic bonded negative electrode

NI-CD

VNT D

High Temperature Series


VNT D

High Temperature Series

STORAGE

Recommended: + 5°C to + 25°C
Relative humidity: 65 ± 5 %

TYPICAL DIMENSIONS



Typical dimensions (mm). Without tube.


The operation of the battery must strictly be in accordance with ARTS Energy technical recommendations, to obtain the performances stated by ARTS Energy.

Data is given for single cells. Please consult ARTS Energy for utilisation of cells outside specification.


Data in this document is subject to change without notice and become contractual only after written confirmation by ARTS Energy.

For graphs shown, C is the IEC₅ capacity.


Charge 24h at C/20 at different temperatures




Discharge at C/5 at different temperatures after charge 16h at C/10 at room temperature



Discharge at 0.6 C after charge 24h at C/20 at different temperatures



Charge efficiency after charge at C/20 and discharge at C/5 at different temperatures



10, rue Ampère
Zone Industrielle - 16440 Nersac, France
Tél. +33(0)5 45 90 35 52 / 35 53
contact@arts-energy.com

Doc No.: 039-A-0417 - Edition: April 2017
ARTS Energy SAS. Stock capital 971.002
RCS Angoulême 792 635 013
Conception in FR by Alain Bruneaud Création



www.arts-energy.com