LM26500-M Primary Li-MnO₂ cell

3 V lithium manganese dioxide C-size spiral cell

The LM26500-M cell is approved for use in the MIDS-LVT. All three cells must be replaced at the same time. Do not mix SAFT LM26500-M cells with other manufacturer's cells.

SaFT LM R6500-N 3V U-Mn02

Benefits

- High drain/ high pulse capability
- High voltage response, stable during most of the lifetime of the application even after long dormant periods
- High capacity at high current and low temperature
- Low self-discharge compatible with long operating life (less than 1% after 1 year of storage at +20°C)
- Superior resistance to corrosion
- Low magnetic signature

Key Features

- Spiral construction
- Hermetic construction with glass to metal seal
- Stainless steel container
- Integrated safety vent
- Equipped with 4.5A resettable PTC
- Safety Shutdown Separator
- Sleeve Mylar for durability
- Non-corrosive electrolyte
- Non-pressurized at room temperature
- Restricted for transport (Class 9)
- RoHS and REACH compliant
- Made in USA

Designed to meet all major quality, safety and environment standards

- Safety: UL 1642 and IEC 60086-4
- Transport: UN 3090 and UN 3091
- Quality: ISO 9001, Saft World Class Continuous program

Applications

Military, MIDS-LVT⁵

NSN

NSN: 6135-01-545-6582

Electrical characteristics	
(Typical values relative to cells stored for one year or l	ess at +30°C max)
Nominal Capacity (at 150mA +20°C 2.0V cut-off) ¹	7.4 Ah
Open circuit voltage (at +20°C)	3.2 V
Nominal voltage (under 1mA at +20°C)	3.0 V
Nominal energy (at 150mA +20°C 2.0 V cut-off)	20.9 Wh
Pulse capability ²	Up to 4.0 A
Recommended maximum continuous current	2.0 A
Operating conditions	
Operating Temperature Range ³	-40°C to +85°C
Storage temperatures Recommended Allowable ⁴	+30°C (86°F) max -55°C to +90°C
Physical Characteristics	
Diameter (max)	26.0 mm
Height (max)	53.5 mm
Typical weight	61 g
Li metal content	approx. 2.8 g
Terminations	
Flat Ni - Plated	

1 Dependent upon current drain, temperature and cut-off


- 2 Dependent upon pulse characteristics, temperature, cell history and application. Higher rates are available under certain circumstances.
- 3 To maintain cell heating within safe limits, Battery packs may imply lower level of maximum current and may require specific thermal protection. Consult Saft.
- 4 Long time storage at high temperature may affect performances. Consult Saft.
- 5 Export License: ECCN 3A611.x export license required to export from the United States.



LM26500-M

LM26500-M dimensions

[1.024 in MAX] Ø 26.0 mm



Storage

 The storage area should be clean, cool (preferably not exceeding +30°C), dry and ventilated.

Warning

- Fire, explosion and burn hazard.
- Do not recharge, short circuit, crush, disassemble, heat above 85°C, incinerate, or expose contents to water.
- Do not solder directly to the cell
- Do not mix Saft LM26500-M cells with other manufacturer's cells.
- All three cells must be replaced at the same time.

Saft


12, rue Sadi Carnot 93170 Bagnolet - France Tel.: +33 (0)1 49 93 19 18 Fax: +33 (0)1 49 93 19 69


Saft America, Inc.


313 Crescent St. Valdese, NC 28690 – USA Tel.: +1 (828) 874 4111 Fax: +1 (828) 874 2431

www.saftbatteries.com

Voltage plateau vs. rate at various temperatures at mid-discharge







Doc. N°: 31175-2-0219 Edition: February 2019

Data in this document is subject to change without Notice and becomes contractual only after written confirmation by Saft.

Published by the Communications Department Photo credit: Saft

